

Engineering the dynamics of topological spin textures by anisotropic spin-orbit torques

J.-P. Hanke^{1,2,*}, F. Freimuth¹, B. Dupé^{3,2}, J. Sinova², M. Kläui² and Y. Mokrousov^{1,2,†}

¹*Peter Grünberg Institut and Institute for Advanced Simulation, Forschungszentrum Jülich and JARA, 52425 Jülich, Germany*

²*Institute of Physics, Johannes Gutenberg University Mainz, 55099 Mainz, Germany*

³*Fonds de la Recherche Scientifique–FNRS, Nanomat/Q-mat/CESAM, Université de Liège, B-4000 Sart Tilman, Belgium*



(Received 5 November 2019; published xxxxxx)

Integrating topologically stabilized magnetic textures such as skyrmions as nanoscale information carriers into future technologies requires the reliable control by electric currents. Here, we uncover that the relevant skyrmion Hall effect, which describes the deflection of moving skyrmions from the current flow direction, acquires important corrections owing to anisotropic spin-orbit torques that alter the dynamics of topological spin structures. Thereby, we propose a viable means for manipulating the current-induced motion of skyrmions and antiskyrmions. Based on these insights, we demonstrate by first-principles calculations and symmetry arguments that the motion of spin textures can be tailored by materials design in magnetic multilayers of Ir/Co/Pt and Au/Co/Pt. Our work advances the understanding of the current-induced dynamics of these magnetic textures, which underlies a plethora of memory and logic applications.

DOI: [10.1103/PhysRevB.00.004400](https://doi.org/10.1103/PhysRevB.00.004400)

I. INTRODUCTION

Magnetic skyrmions are topologically stabilized spin textures that hold bright promises as robust processing units in innovative information technologies. In particular, the prospects of using these noncollinear magnetic structures in efficient racetrack memories [1] or for brain-inspired computing [2,3] have sparked tremendous interest in the research field. Ever since, generating these localized spin structures, moving them at high speeds, and detecting them by electrical means constitute the key objectives for realizing competitive skyrmion-based devices. Only recently, it has been experimentally demonstrated that individual skyrmions can form at room temperature [4–6] due to an enhanced thermal stability in carefully designed magnetic superlattices, for instance, of Pt/CoFeB/MgO or Ir/Co/Pt. In these systems combining spatial inversion asymmetry with strong spin-orbit coupling, the stabilization of topological spin textures originates from the Dzyaloshinskii-Moriya interaction (DMI) [7,8]. Its interfacial nature renders this chiral exchange interaction tunable in the magnetic multilayers via appropriate materials engineering [9–11], which facilitates the versatile control over static texture properties including skyrmion radius and chirality [12,13].

The challenge of displacing these chiral magnetic structures by purely electrical means is usually addressed by exploiting the phenomenon of spin-orbit torques (SOTs) [14]. These torques contain two qualitatively distinct contributions, namely, a fieldlike term T^{FL} and an antidamping term T^{AD} , both of which root in relativistic spin-orbit effects in systems that lack spatial inversion symmetry. Specifically,

charge currents can trigger an interfacial spin polarization in these systems, exerting SOTs on the local magnetization [15–19], which facilitates switching of ferro- and antiferromagnets [20–22] as well as moving of domain walls and skyrmions [4,23–25]. However, owing to their nontrivial topology in two-dimensional real space, skyrmions move under an angle θ_{sk} with respect to the line of the applied current [24,25]. This so-called skyrmion Hall effect obstructs the immediate use of skyrmionic spin structures in racetrack devices, e.g., for logic functionalities, as they suffer intrinsically from deflections. Shaping the complex trajectory of topological spin textures fundamentally relies on our microscopic understanding of the interplay between spin topology, damping, and current-induced SOTs [26]. While the Thiele equation of motion [27,28] accounts for this interplay, the corresponding treatment led to the common perception that a whole class of SOTs—the fieldlike torques—is irrelevant for describing the dynamical properties of rigid skyrmions as well as the skyrmion Hall effect.

In this work, we demonstrate that this widely accepted picture needs to be extended owing to the nontrivial form of SOTs in magnetic multilayers. While the current-induced dynamics of skyrmions was previously explained based on deformations of the spin texture [25], here, we promote a distinct mechanism to activate fieldlike SOTs. We show that the anisotropy of these torques plays an important role for predicting and interpreting the dynamics of topological spin structures. Specifically, we uncover that the coupling of magnetic textures to fieldlike torques which are higher order in the local magnetization can manifest in large corrections to the skyrmion Hall effect. Using first-principles calculations and symmetry arguments, we quantify the relevance of these modifications for the dynamical properties of skyrmions and antiskyrmions in layered magnetic films of Ir/Co/Pt and Au/Co/Pt, as described by the Thiele equation. Our findings

*j.hanke@fz-juelich.de

†y.mokrousov@fz-juelich.de

1 outline a perspective for controlling the skyrmion Hall effect and the motion of skyrmions or antiskyrmions in multilayer systems by engineering the anisotropy of the SOTs.

2 The article is structured as follows. In Sec. II, we review the Thiele equation of current-induced skyrmion motion, elucidate the symmetry-allowed form of SOTs based on effective magnetic fields, and provide the details of our first-principles calculations. The resulting anisotropies of the torques in the magnetic trilayers are presented in Sec. III, where we discuss also their imprint on the forces and skyrmion Hall angle of topological spin textures. Section IV concludes this work.

II. METHODS

A. Thiele equation of skyrmion motion

3 Treating skyrmions as rigid objects in a ferromagnetic background, the Thiele equation [27,28] describes the dynamical properties of unit-vector magnetization fields $\mathbf{m}(\mathbf{r})$ with nontrivial topology in two-dimensional real space:

$$(QA - D)\mathbf{v} = \mathbf{F}, \quad (1)$$

4 where $\mathbf{v} = (v_x, v_y)$ is the velocity of the skyrmions. The gyromagnetic term $QA\mathbf{v}$ in Eq. (1) is mediated by the anti-symmetric tensor $A_{ij} = \epsilon_{ij}$ with the Levi-Civita symbol ϵ_{ij} and the integer topological charge

$$Q = (1/4\pi) \int_{\mathbb{R}^2} \mathbf{m} \cdot (\partial_x \mathbf{m} \times \partial_y \mathbf{m}) d\mathbf{r}. \quad (2)$$

5 Additionally, the magnetization dynamics are affected by the dissipative coupling $-D\mathbf{v}$, which stems from

$$D_{ij} = (\alpha_G/4\pi) \int_{\mathbb{R}^2} (\partial_i \mathbf{m} \cdot \partial_j \mathbf{m}) d\mathbf{r}, \quad (3)$$

6 where α_G is the Gilbert damping and $\partial_i \mathbf{m} = \partial \mathbf{m} / \partial r_i$ denotes the spatial gradient of the spin texture along the i th Cartesian direction. While gyromagnetic and dissipative terms root manifestly in the local variations of $\mathbf{m}(\mathbf{r})$ in real space, the generalized force $\mathbf{F} = (F_x, F_y)$ on the right-hand side of Eq. (1) reflects the interaction of current-induced torques $\mathbf{T}(\mathbf{m})$ with the magnetic texture:

$$F_i = \frac{1}{4\pi} \int_{\mathbb{R}^2} \mathbf{T}(\mathbf{m}) \cdot (\partial_i \mathbf{m} \times \mathbf{m}) d\mathbf{r}. \quad (4)$$

7 To arrive at this expression, locally, the spin polarization perpendicular to \mathbf{m} is expressed as $\mathbf{s}_\perp = \mathbf{m} \times \mathbf{T}(\mathbf{m})$ [29].

8 Using polar coordinates $\mathbf{r} = (\rho, \phi)$, we focus in this work on Néel skyrmions with a radially symmetric profile as given by $\mathbf{m}(\rho, \phi) = [\cos \phi \sin \Theta(\rho), \sin \phi \sin \Theta(\rho), \cos \Theta(\rho)]$ that is characterized by the position-dependent angle [30]

$$\Theta(\rho) = \arcsin \left(\tanh \frac{c - \rho}{w/2} \right) - \arcsin \left(\tanh \frac{c + \rho}{w/2} \right). \quad (5)$$

9 Here, the parameter c represents the size of the skyrmion core and w denotes the width of the domain wall, which we will use below as the intrinsic length scale for the real-space quantities ρ and c . A schematic of the radial profile is shown in Fig. 3(a).

B. Spin-orbit torques and effective fields

10 According to Eq. (4), current-induced torques acting on the magnetization constitute the key information in

11 understanding and predicting the dynamical properties of spin textures based on the Thiele equation. Restricting our analysis here to the case of spin-orbit torques (SOTs), we distinguish two qualitatively distinct contributions to these phenomena, namely, the fieldlike torque $\mathbf{T}^{\text{FL}}(\mathbf{m}) = \mathbf{m} \times \mathbf{H}_{\text{eff}}^{\text{FL}}(\mathbf{m})$ and the antidamping torque $\mathbf{T}^{\text{AD}}(\mathbf{m}) = \mathbf{m} \times \mathbf{H}_{\text{eff}}^{\text{AD}}(\mathbf{m})$, which can be related to effective magnetic fields that are routinely used to quantify SOTs in experiment. While the fieldlike component of the torque changes its sign under magnetization reversal, the antidamping one is invariant, which is also reflected in the microscopic form of the fields $\mathbf{H}_{\text{eff}}^{\text{FL}}$ and $\mathbf{H}_{\text{eff}}^{\text{AD}}$.

12 All of the symmetry-allowed terms in the magnetization dependence of the fieldlike and antidamping torques, entering Eq. (4), can be obtained systematically by applying the so-called Neumann's principle [31]. When interpreting the SOTs as linear response to the electric field \mathbf{E} , the corresponding effective magnetic fields assume the forms

$$\mathbf{H}_{\text{eff},i}^{\text{FL}} = \alpha_{ij} E_j + \alpha_{ijkl} E_j m_k m_l + \dots, \quad (6)$$

$$\mathbf{H}_{\text{eff},i}^{\text{AD}} = \beta_{ijk} E_j m_k + \beta_{ijkln} E_j m_k m_l m_n + \dots. \quad (7)$$

13 Here, summation over repeated indices is implied, and the axial tensors α as well as the polar tensors β follow the symmetries of the underlying crystal lattice according to Neumann's principle. While the effective fields for the fieldlike torques originate from axial tensors of even rank, their antidamping analogs root in the polar tensors of odd rank. Thus, if the electric field is oriented along the x direction within the plane of the two-dimensional film, the effective fields are $\mathbf{H}_{\text{eff}}^{\text{FL}}(\mathbf{m}) \propto \hat{e}_y$ and $\mathbf{H}_{\text{eff}}^{\text{AD}}(\mathbf{m}) \propto (\mathbf{m} \times \hat{e}_y)$ to lowest order. We demonstrate below that nontrivial higher-order terms in the expansions, which go beyond these conventionally used lowest-order expressions, are important as they modify the dynamical properties of topological spin textures.

14 Depending on the symmetry of a given system, each tensor in Eqs. (6) and (7) may contain several free parameters that are specific to the electronic structure of the material. In order to determine these parameters from first principles, we evaluate first the torkance tensor $\tau(\mathbf{m})$, which relates the SOTs to the applied electric field via $T_i(\mathbf{m}) = \sum_j \tau_{ij}(\mathbf{m}) E_j$ [19]. The shape of the torkance tensor itself depends on the crystal symmetry and on the magnetization direction. For example, the fieldlike torkance is proportional to the unit matrix for films with C_{3v} symmetry and perpendicular magnetization, whereas the antidamping torkance amounts to an antisymmetric tensor in this case. Based on linear response theory, the (even) antidamping torkance is given by [19]

$$\begin{aligned} \tau_{ij}^{\text{AD}} = & \frac{e\hbar}{2\pi N} \sum_{kn} \sum_{m \neq n} \text{Im} [\langle \psi_{kn} | \mathcal{T}_i | \psi_{km} \rangle \langle \psi_{km} | v_j | \psi_{kn} \rangle] \\ & \times \left\{ \frac{\Gamma(\mathcal{E}_{km} - \mathcal{E}_{kn})}{[(\mathcal{E}_F - \mathcal{E}_{kn})^2 + \Gamma^2][(\mathcal{E}_F - \mathcal{E}_{km})^2 + \Gamma^2]} \right. \\ & + \frac{2\Gamma}{[\mathcal{E}_{kn} - \mathcal{E}_{km}][(\mathcal{E}_F - \mathcal{E}_{km})^2 + \Gamma^2]} \\ & \left. + \frac{2}{(\mathcal{E}_{kn} - \mathcal{E}_{km})^2} \text{Im} \ln \frac{\mathcal{E}_{km} - \mathcal{E}_F - i\Gamma}{\mathcal{E}_{kn} - \mathcal{E}_F - i\Gamma} \right\} \quad (8) \end{aligned}$$




FIG. 1. (a),(b) Top and side views of the considered magnetic films that consist of Pt(111) underlayers (dark gray), a magnetic Co monolayer (light gray), and heavy-metal overlayers (dark red) such as Ir or Au. Bold integers label the different overlayers to highlight the C_{3v} symmetry around the z axis. Red arrows in (b) indicate the direction of the magnetic moment of Co. (c) Variation of the spin-orbit torques τ_{yx} (red circles) and $-\tau_{xx}$ (blue squares) when alloying the overlayers from Ir over Pt to Au in the perpendicularly magnetized system. The effect of alloying is treated within the virtual crystal approximation.

170 and the (odd) fieldlike torque amounts to [19]

$$\tau_{ij}^{\text{FL}} = \frac{e\hbar}{\pi N} \sum_{knm} \frac{\Gamma^2 \text{Re}[\langle \psi_{kn} | \mathcal{T}_i | \psi_{km} \rangle \langle \psi_{km} | v_j | \psi_{kn} \rangle]}{[(\mathcal{E}_F - \mathcal{E}_{kn})^2 + \Gamma^2][(\mathcal{E}_F - \mathcal{E}_{km})^2 + \Gamma^2]}, \quad (9)$$

171 where N is the number of \mathbf{k} points, $|\psi_{kn}\rangle$ is the Bloch
 172 state with the band energy \mathcal{E}_{kn} , the Fermi energy is \mathcal{E}_F , and
 173 Γ is a constant band broadening that models the effect of
 174 disorder. In addition, $\hbar\mathbf{v} = \nabla_{\mathbf{k}}H(\mathbf{k})$ and $\mathcal{T} = \mathbf{m} \times \nabla_{\mathbf{m}}H(\mathbf{k})$
 175 denote velocity and torque operators, respectively, which re-
 176 late to momentum and magnetization derivatives of the lattice-
 177 periodic Hamiltonian. Then, by fitting the analytical forms of
 178 the torques due to Eqs. (6) and (7) to first-principles data for
 179 the corresponding torques, we extract the material-specific
 180 parameters that enter Neumann's expansion of the effective
 181 magnetic fields. Thereby, we can gain microscopic insights
 182 into the magnetization dependence of the SOTs, which allows
 183 us to assess their roles for the dynamics of rigid spin structures
 184 as governed by the Thiele equation (1).

185 C. Details of first-principles calculations

186 Using the full-potential linearized augmented-plane-wave
 187 (FLAPW) method as implemented in the FLEUR code [32],
 188 we perform density functional theory calculations of the
 189 electronic structure of thin ferromagnetic films. Specifically,
 190 we consider hexagonal magnetic trilayers which consist of a
 191 Co monolayer between four Pt(111) layers and four alloyed
 192 heavy-metal layers that contain Ir or Au; see Figs. 1(a)
 193 and 1(b). The effect of alloying is accounted for by changing
 194 the nuclear charges of the overlayers under the constraint
 195 of charge neutrality within the virtual crystal approxima-
 196 tion (VCA) [33]. The structural parameters of Ref. [11] are
 197 adopted, and exchange-correlation effects are treated within
 198 the generalized gradient approximation [34]. We choose a
 199 muffin-tin radius of $2.23a_0$ for Co and $2.29a_0$ for all other
 200 atom types, where a_0 refers to Bohr's radius. The plane-
 201 wave cutoff is set to $4.0a_0^{-1}$ and spin-orbit coupling is in-
 202 cluded self-consistently. In the studied ferromagnetic systems

with C_{3v} crystal symmetry, the magnetization direction $\mathbf{m} =$
 203 $(\cos\varphi \sin\theta, \sin\varphi \sin\theta, \cos\theta)$ is represented in spherical co-
 204 ordinates by the polar angle θ and the azimuthal angle φ .
 205

206 After converging charge and spin densities of the trilayers,
 207 we exploit the obtained wave-function information on an
 208 equidistant \mathbf{k} mesh of 8×8 points for eight different values
 209 of θ or φ in $[0, 2\pi)$ in order to construct higher-dimensional
 210 Wannier functions (HDWFs) [35]. Based on a customized
 211 version of the WANNIER90 code [36], we generate a single
 212 set of 162 HDWFs out of 228 Bloch bands, with the frozen
 213 window extending up to 2 eV above the Fermi energy. The
 214 representation of the Hamiltonian in the basis of HDWFs
 215 allows us to efficiently access the full dependence of the SOTs
 216 on θ and φ via a generalized Wannier interpolation [11,35].
 217 To obtain accurate values for the fieldlike and antidamping
 218 torques for arbitrary magnetization directions, we sample
 219 the momentum Brillouin zone with a dense mesh of $512 \times$
 220 512 points to carry out the \mathbf{k} summation in Eqs. (8) and (9).
 221 Furthermore, we employ a broadening of $\Gamma = 25$ meV to
 222 model the effect of disorder on the energy bands.

223 III. RESULTS

224 A. Effect of heavy-metal overlayers

225 First, we discuss how the fieldlike and antidamping SOTs
 226 are modified as we consider different alloys for the heavy-
 227 metal overlayers of the perpendicularly magnetized system
 228 with $\theta = \varphi = 0^\circ$. Figure 1(c) reveals that the antidamping
 229 torque τ_{yx} is rather susceptible to the corresponding changes
 230 of the electronic structure, which directly correlates with the
 231 prominent sensitivity of the Dzyaloshinskii-Moriya interac-
 232 tion with respect to alloying [11]. However, the computed val-
 233 ues of τ_{yx} are nearly identical in the stoichiometric Ir/Co/Pt
 234 and Au/Co/Pt films, which lack spatial inversion symmetry.
 235 In sharp contrast, the larger fieldlike response τ_{xx} follows
 236 an approximately linear trend with alloy composition, see
 237 Fig. 1(c), resulting in torques of similar magnitude but
 238 opposite sign in the two stoichiometric cases. We focus in the
 239 following discussion on the trilayers Ir/Co/Pt and Au/Co/Pt.




FIG. 2. (a),(b) First-principles dependence of (a) antidamping and (b) fieldlike torque tensors on the magnetization direction in the ferromagnetic trilayer Ir/Co/Pt. The angles θ and φ are used to characterize the magnetization direction $\mathbf{m} = (\cos \varphi \sin \theta, \sin \varphi \sin \theta, \cos \theta)$ in spherical coordinates. Filled circles, squares, and triangles denote data for the xx , yx , and zx elements of the tensors, respectively, and solid lines represent corresponding fits according to the Neumann expansion. (c),(d) Same as in panels (a) and (b) but for Au/Co/Pt.

B. Anisotropy of spin-orbit torques

We begin with elucidating the magnetization dependence of the spin-orbit torque tensors in the ferromagnetic trilayers for the example of an applied electric field along the x direction. Using the above usual lowest-order expressions for the effective fields $\mathbf{H}_{\text{eff}}^{\text{FL}}$ and $\mathbf{H}_{\text{eff}}^{\text{AD}}$, we expect that the xx element of the odd fieldlike torque follows a curve like $\tau_{xx}^{\text{FL}} \propto \cos \theta$ if $\varphi = 0^\circ$, whereas the even antidamping torque τ_{yx}^{AD} should amount to a constant value in this case.

Our first-principles results shown in Fig. 2 clearly demonstrate that, in fact, this simple picture does not hold in Ir/Co/Pt and Au/Co/Pt, indicating that higher-order torques which are allowed by symmetry play an important role. In particular, the even antidamping is strongly anisotropic with respect to the magnetization direction, Figs. 2(a) and 2(c), and its functional form is qualitatively different in the two layered systems owing to distinct spin-orbit hybridizations of the states near the Fermi energy. Analogously, the angular dependence of the odd torque τ_{xx}^{FL} in Figs. 2(b) and 2(d) departs from the ideal cosinelike shape, irrespective of the considered heavy-metal overlayer which determines the overall sign of the fieldlike torque. However, while the odd torque is nearly one order of magnitude larger than its even counterpart, the deviation from the anticipated lowest-order behavior is less prominent than for the antidamping torque.

By fitting the corresponding Neumann expansions for the effective fields for the case of C_{3v} crystal symmetry to our complete data, we reveal that higher-order terms (i.e., polar tensors of rank five) are indeed necessary to describe the computed angular dependence of the antidamping SOTs. Specifically, we find that the effective field $\mathbf{H}_{\text{eff}}^{\text{AD}} \propto (0, 0, m_x^2 m_z)$ constitutes the first important torque correction with a similar

value of the corresponding free parameter in the systems Ir/Co/Pt and Au/Co/Pt. For example, this qualitatively distinct higher-order correction amounts to as much as 40% of the leading order in Ir/Co/Pt, which underlines its relevance for understanding the magnetization dependence of antidamping SOTs. In the case of the fieldlike torques, the same fitting procedure predicts that the effective field $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto \hat{e}_y$ describes the SOT data to first approximation rather well. However, a more detailed analysis uncovers that higher-order contributions beyond this leading-order term are present in both systems, as encoded in axial tensors of rank four in Eq. (6) that give rise to SOT fields like $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto (2m_x m_y, -3m_x^2 - m_y^2, 0)$ and $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto (0, -m_z^2, 0)$. For the example of Ir/Co/Pt, these terms amount to relative strengths of about 30% and 20% of the leading order, respectively. The anisotropic fieldlike torques which result from these fields will play a key role for the dynamical properties of topological spin textures.

C. Generalized forces on spin textures

Next, we turn to the Thiele equation of motion and evaluate the generalized forces therein which originate from the current-induced torques according to Eq. (4). Leaving aside the effect of spin-transfer torques for future work, here we aim to uncover the fundamental signatures of SOTs for the dynamical properties of topological spin structures. For this purpose, we assume that the electronic structure of nontrivial spin textures follows locally the one of the ferromagnetic state with a given direction \mathbf{m} such that we can exploit our first-principles SOT data to calculate the torque-driven forces. In particular, we focus on the coupling of SOTs to radially symmetric Néel-type skyrmions following the magnetization profile given by Eq. (5) with $c = w/2$; see also Fig. 3(a).




FIG. 3. (a) General, radially symmetric Néel-type skyrmion profile with core size c and width w of the domain wall. Colors encode the out-of-plane component of the local magnetization. (b),(c) Skyrmions and antiskyrmions are subject to current-induced forces that act parallel (F_{\parallel}) or perpendicular (F_{\perp}) to the current flow direction. Green and yellow colors correspond to clockwise and counterclockwise rotational senses along the radial direction, respectively, and the brightness denotes the out-of-plane spin component. (d),(e) Forces F_{\parallel} (dashed blue line) and F_{\perp} (solid red line), per electric field E , on the radially symmetric Néel skyrmion in the magnetic trilayers (d) Ir/Co/Pt and (e) Au/Co/Pt. The position of the Fermi energy is varied, the value of the force F_{\perp} perpendicular to the electric-field direction is scaled by a factor of four, and $c = w/2$ is used in (d)–(g). (f),(g) Real-space distribution of the force density f_{\perp} in (f) Ir/Co/Pt and (g) Au/Co/Pt for the self-consistent value of the Fermi energy. Bold integers as well as circles of increasing radius indicate the radial distance ρ in units of w , the skyrmion core is located in the center, and the arrow points along the electric field \mathbf{E} . The black circle denotes the radius for which the out-of-plane component of the magnetization is zero.

addition, we remark that the characteristic angular behavior of the antidamping torques manifests exclusively in a parallel force component for symmetric spin textures, whereas the force F_{\perp} is completely determined by the fieldlike SOTs.

Although the magnitude of the fieldlike torques is generally larger (see Fig. 2), the resulting forces are a factor of four smaller than those due to the antidamping SOTs. This can be understood by analyzing in detail the form of Eq. (4) when taking into account the expansions in Eqs. (6) and (7). While the effective field $\mathbf{H}_{\text{eff}}^{\text{AD}}$ generates a finite force already at its lowest order, it is straightforward to show that the fieldlike SOT mediated by $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto \hat{\mathbf{e}}_y$ results in no force on the rigid symmetric spin texture. As a consequence, the less prominent higher-order terms of $\mathbf{H}_{\text{eff}}^{\text{FL}}$ constitute the only sources for the nonzero transverse force F_{\perp} in Figs. 3(d) and 3(e) due to the fieldlike torques. Therefore, by controlling the anisotropy of the corresponding effective SOT fields, we could engineer the magnitude of the force that acts perpendicular to the current line. Alternatively, we note that the inoperative leading order of the fieldlike torques would become active again if the spin texture is deformed as is often observed in experiment (see, for example, Ref. [25]).

Based on our first-principles results shown in Figs. 3(d) and 3(e), we identified the polar and axial effective fields that yield the most dominant contributions to the torque-driven forces. In both systems Ir/Co/Pt and Au/Co/Pt, the largest terms due to the fieldlike SOTs originate from the effective fields $\mathbf{H}_{\text{eff}}^{\text{FL}}$ that behave like $(2m_x m_y, -3m_x^2 - m_y^2, 0)$, $(0, -m_z^2, 0)$, and $(m_x m_y, m_z^2, 0)$, given in descending order of relevance for the forces. In the case of the antidamping SOTs, similarly, we find that the effective fields $\mathbf{H}_{\text{eff}}^{\text{AD}}$ which are proportional to $(m_z, 0, 0)$, $(0, 0, m_x)$, and $(0, 0, m_x^2 m_z)$ constitute the most important parts of the forces in the considered films.

We present in Figs. 3(f) and 3(g) the real-space distributions of the density f_{\perp} as the integrand in Eq. (4) that sums up to the transverse generalized force F_{\perp} . The panels uncover that this force density, which reflects the nontrivial angular dependence of the anisotropic fieldlike SOTs, is distributed asymmetrically with a generic orientation that is set by the underlying electronic structure of the crystal.

To elucidate more clearly the overall relevance of the proposed mechanism based on anisotropic fieldlike torques, we consider the effect of deformations of the skyrmion texture on the generalized forces. For this purpose, we assume a deformed spin structure by replacing the constant core size c in Eq. (5) with $c + \delta c \sin^2 \phi$, where δc encodes the degree of deviation from the symmetric profile, which is recovered for $\delta c = 0$. While any finite deformation of this type indeed activates perpendicular forces mediated by the lowest-order effective field $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto \hat{\mathbf{e}}_y$, rather strong modifications of the spin structure are necessary to change F_{\perp} considerably as shown in Fig. 4. However, the additional lowest-order fieldlike torque hardly alters the dynamics of topological spin textures if only small to medium deformations are present, in the case of which F_{\perp} originates primarily from anisotropic fieldlike SOTs. At the same time, we note that the force F_{\parallel} due to the antidamping torques remains essentially unchanged for the considered type of deformations of the skyrmion structure.

Figure 3 summarizes our first-principles results for the generalized in-plane forces which act parallel (F_{\parallel}) or perpendicular (F_{\perp}) to the applied electric field. The calculated dependence of these forces on the position of the Fermi energy in Figs. 3(d) and 3(e) reveals that they are susceptible to changes of the local electronic structure. Thus doping of the heavy-metal overlayer provides a suitable means for tailoring the magnitude and the sign of these dynamical forces. In




FIG. 4. Deformations of the skyrmion profile activate additional contributions to the perpendicular force F_{\perp} in (a) Ir/Co/Pt and (b) Au/Co/Pt. The shaded area denotes the force for the rigid symmetric texture, whereas solid blue ($\delta c = 0.1w$) and solid red ($\delta c = 0.2w$) lines represent the corresponding changes owing to deformations of the spin profile via the modulated core size $c + \delta c \sin^2 \phi$. In the case of $\delta c = 0.2w$, the dashed black line indicates the new force component due to the lowest-order fieldlike torque.

D. Skyrmion Hall effect

Using our microscopic insights into the generalized forces and the fundamental effective SOT fields, we address now the question of how the higher-order torques affect the dynamical properties of Néel-type skyrmions. Owing to the interplay of gyromagnetic coupling, dissipation, and generalized forces in the Thiele equation (1), topological spin textures usually move under an angle with respect to the applied electric field. As the magnetic analog of the Magnus effect, this so-called skyrmion Hall effect stems from the complex spin topology in real space, and it is quantified by the skyrmion Hall angle $\theta_{\text{sk}} = \arctan v_{\perp}/v_{\parallel}$. Since the dissipation tensor, Eq. (3), amounts to the unit matrix times a constant $D = \mathcal{D}_{xx} = \mathcal{D}_{yy}$ for the considered symmetric magnetic texture, we arrive at

$$\frac{v_{\perp}}{v_{\parallel}} = \frac{QF_{\parallel} + DF_{\perp}}{DF_{\parallel} - QF_{\perp}} = \frac{Q}{D} + \frac{(D + Q^2/D)F_{\perp}}{DF_{\parallel} - QF_{\perp}}. \quad (10)$$

Therefore, while θ_{sk} is determined solely by Q/D in the absence of any transverse torque-related force, in fact, the second equality emphasizes that the skyrmion Hall angle acquires a correction due to the force F_{\perp} that can be activated either by the presence of higher-order fieldlike SOTs (see Fig. 3), or by deformations of the spin structure.

Figure 5 presents the computed energy dependence of the skyrmion Hall angle θ_{sk} in the considered magnetic trilayers Ir/Co/Pt and Au/Co/Pt, for which we assume a constant Gilbert parameter of $\alpha_G = 0.05$ as the Ir/Co and Au/Co interfaces exhibit similar damping characteristics [37,38]. Our calculations show that while θ_{sk} is generally finite, which corresponds to a deflection of the symmetric skyrmion from the current line, proper engineering of the electronic structure facilitates in principle a straight motion of the spin structure without suffering from any skyrmion Hall effect. This is possible as the transverse force component that is triggered by higher-order fieldlike SOTs adds crucial flexibility for balancing the different terms in the Thiele equation of motion. For example, doping Au with Pt or substituting a small portion of Ir with Os can thus drastically change the skyrmion Hall angle, see Fig. 5(b), as compared to the case without anisotropic torques, where θ_{sk} relates to Q/D .




FIG. 5. (a) Due to the skyrmion Hall effect, skyrmions and antiskyrmions move under the angle θ_{sk} with respect to the applied electric field E . The color scale for the spin textures follows the one of Fig. 3. (b) Skyrmion Hall angle θ_{sk} in the magnetic trilayers Ir/Co/Pt (solid red line) and Au/Co/Pt (dashed blue line) as the Fermi energy is varied. The results are obtained by considering the symmetry-allowed first-principles shape of the spin-orbit torques. For comparison, the thin gray line indicates the value of θ_{sk} in the absence of anisotropic fieldlike torques. The chosen Gilbert damping parameter of $\alpha_G = 0.05$ is assumed to be independent of the energy.

Finally, we remark that our conclusions apply analogously to antiskyrmions [13,39], which can be obtained by reflecting the magnetization profile (5) at a plane perpendicular to the film. Specifically, the symmetric Néel texture shown in Fig. 2(b) transforms into the spin structure of an antiskyrmion if the corresponding magnetization field is mirrored at the $y = 0$ plane; see Fig. 2(c). Thus, in the rigid body approximation, if the Néel skyrmion moves under the angle θ_{sk} , the antiskyrmion exhibits the very same Hall angle but with respect to an accordingly mirrored axis as illustrated in Fig. 5(a), although the dynamics of antiskyrmions can generally be more complex than for skyrmions [26].

IV. CONCLUSIONS

Using material-specific electronic-structure calculations in combination with symmetry considerations for the effective magnetic fields, we demonstrated that the anisotropy of spin-orbit torques (SOTs) is vital in understanding and predicting the dynamical properties of topological spin textures. In particular, we uncovered that higher orders of the fieldlike SOTs manifest in qualitatively new forces that act transverse to an applied electric field. These anisotropic fieldlike torques couple to the motion of radially symmetric Néel-type skyrmions and antiskyrmions, and imprint on their dynamics, granting thereby additional flexibility in tuning the skyrmion Hall angle in real multilayer materials. Considering as specific examples the film systems Ir/Co/Pt and Au/Co/Pt, we showed that substitutional doping of the overlayers with other heavy metals provides indeed a suitable means for engineering the dynamics of magnetic textures.

Our findings open up an alternative path for controlling the motion of skyrmions by proper materials design of anisotropic SOTs. The predicted phenomenon competes with the conventional mechanism where the isotropic field $\mathbf{H}_{\text{eff}}^{\text{FL}} \propto \hat{e}_y$ can effectively couple to the spin structure due to deformations of the texture. Developing a coherent picture of the interplay of these two competing effects beyond the limited treatment of

444 the Thiele equation, for example, by atomistic spin dynamics
 445 simulations, presents an exciting research direction. However,
 446 this necessitates the extension of such simulations to incorpo-
 447 rate the relevant effective SOT fields that are of higher order
 448 in the local magnetization. Overall, our microscopic insights
 449 into the dynamical properties of skyrmions and antiskyrmions
 450 call for reviewing the common perception that the skyrmion
 451 Hall effect is independent of the fieldlike SOT. Specifically,
 452 this phenomenon could acquire large corrections in systems
 453 with reduced symmetry owing to the proposed mechanism
 454 that roots in the prominent anisotropy of fieldlike torques.

ACKNOWLEDGMENTS

We thank Markus Hoffmann and Stefan Blügel for insight-
 ful discussions, and we acknowledge support by the Deutsche
 Forschungsgemeinschaft (DFG) through Priority Programm
 No. SPP 2137 and the Collaborative Research Center No.
 SFB/TRR 173. Y.M. acknowledges funding from the DARPA
 TEE program through Grant MIPR (No. HR0011831554)
 from DOI. We also gratefully acknowledge the Jülich Super-
 computing Centre and RWTH Aachen University for provid-
 ing computational resources under project jiff40.

- [1] A. Fert, V. Cros, and J. Sampaio, *Nat. Nanotechnol.* **8**, 152 (2013).
- [2] G. Bourianoff, D. Pinna, M. Sitte, and K. Everschor-Sitte, *AIP Adv.* **8**, 55602 (2018).
- [3] J. Zázvorka, F. Jakobs, D. Heinze, N. Keil, S. Kromin, S. Jaiswal, K. Litzius, G. Jakob, P. Virnau, D. Pinna, K. Everschor-Sitte, L. Rózsa, A. Donges, U. Nowak, and M. Kläui, *Nat. Nanotechnol.* **14**, 658 (2019).
- [4] S. Woo, K. Litzius, B. Krüger, M.-Y. Im, L. Caretta, K. Richter, M. Mann, A. Krone, R. M. Reeve, M. Weigand, P. Agrawal, I. Lemesch, M.-A. Mawass, P. Fischer, M. Kläui, and G. S. D. Beach, *Nat. Mater.* **15**, 501 (2016).
- [5] C. Moreau-Luchaire, C. Moutafis, N. Reyren, J. Sampaio, C. A. F. Vaz, N. Van Horne, K. Bouzehouane, K. Garcia, C. Deranlot, P. Warnicke, P. Wohlhüter, J.-M. George, M. Weigand, J. Raabe, V. Cros, and A. Fert, *Nat. Nanotechnol.* **11**, 444 (2016).
- [6] K. Everschor-Sitte, J. Masell, R. M. Reeve, and M. Kläui, *J. Appl. Phys.* **124**, 240901 (2018).
- [7] I. Dzyaloshinsky, *J. Phys. Chem. Solids* **4**, 241 (1958).
- [8] T. Moria, *Phys. Rev.* **120**, 91 (1960).
- [9] A. Hrabec, N. A. Porter, A. Wells, M. J. Benitez, G. Burnell, S. McVitie, D. McGrouther, T. A. Moore, and C. H. Marrows, *Phys. Rev. B* **90**, 020402(R) (2014).
- [10] H. Yang, A. Thiaville, S. Rohart, A. Fert, and M. Chshiev, *Phys. Rev. Lett.* **115**, 267210 (2015).
- [11] J.-P. Hanke, F. Freimuth, S. Blügel, and Y. Mokrousov, *J. Phys. Soc. Jpn.* **87** 041010 (2018).
- [12] L. Camosi, S. Rohart, O. Fruchart, S. Pizzini, M. Belmeguenai, Y. Roussigné, A. Stashkevich, S. M. Cherif, L. Ranno, M. de Santis, and J. Vogel, *Phys. Rev. B* **95**, 214422 (2017).
- [13] M. Hoffmann, B. Zimmermann, G. P. Müller, D. Schürhoff, N. S. Kiselev, C. Melcher, and S. Blügel, *Nat. Commun.* **8**, 308 (2017).
- [14] A. Manchon, J. Železný, I. M. Miron, T. Jungwirth, J. Sinova, A. Thiaville, K. Garello, and P. Gambardella, *Rev. Mod. Phys.* **91**, 035004 (2019).
- [15] A. Chernyshov, M. Overby, X. Liu, J. K. Furdyna, Y. Lyanda-Geller, and L. P. Rokhinson, *Nat. Phys.* **5**, 656 (2009).
- [16] I. M. Miron, G. Gaudin, S. Auffret, B. Rodmacq, A. Schuhl, S. Pizzini, J. Vogel, and P. Gambardella, *Nat. Mater.* **9**, 230 (2010).
- [17] I. M. Miron, T. Moore, H. Szabolcs, L. D. Buda-Prejbeanu, S. Auffret, B. Rodmacq, S. Pizzini, J. Vogel, M. Bonfim, A. Schuhl, and G. Gaudin, *Nat. Mater.* **10**, 419 (2011).
- [18] K. Garello, I. M. Miron, C. O. Avci, F. Freimuth, Y. Mokrousov, S. Blügel, S. Auffret, O. Boulle, G. Gaudin, and P. Gambardella, *Nat. Nanotechnol.* **8**, 587 (2013).
- [19] F. Freimuth, S. Blügel, and Y. Mokrousov, *Phys. Rev. B* **90**, 174423 (2014).
- [20] I. M. Miron, K. Garello, G. Gaudin, P.-J. Zermatten, M. V. Costache, S. Auffret, S. Bandiera, B. Rodmacq, A. Schuhl, and P. Gambardella, *Nature (London)* **476**, 189 (2011).
- [21] L. Liu, O. J. Lee, T. J. Gudmundsen, D. C. Ralph, and R. A. Buhrman, *Phys. Rev. Lett.* **109**, 096602 (2012).
- [22] P. Wadley, B. Howells, J. Zelezny, C. Andrews, V. Hills, R. P. Campion, V. Novak, F. Freimuth, Y. Mokrousov, A. W. Rushforth, K. W. Edmonds, B. L. Gallagher, and T. Jungwirth, *Science* **351**, 587 (2016).
- [23] R. Tomasello, E. Martinez, R. Zivieri, L. Torres, M. Carpentieri, and G. Finocchio, *Sci. Rep.* **4**, 6784 (2014).
- [24] W. Jiang, P. Upadhyaya, W. Zhang, G. Yu, M. B. Jungfleisch, F. Y. Fradin, J. E. Pearson, Y. Tserkovnyak, K. L. Wang, O. Heinonen, S. G. E. te Velthuis, and A. Hoffmann, *Science* **349**, 283 (2015).
- [25] K. Litzius, I. Lemesch, B. Krüger, P. Bassirian, L. Caretta, K. Richter, F. Büttner, K. Sato, O. A. Tretiakov, J. Förster, R. M. Reeve, M. Weigand, I. Bykova, H. Stoll, G. Schütz, G. S. D. Beach, and M. Kläui, *Nat. Phys.* **13**, 170 (2017).
- [26] U. Ritzmann, S. Von Malottki, J.-V. Kim, S. Heinze, J. Sinova, and B. Dupé, *Nat. Electron.* **1**, 451 (2018).
- [27] A. A. Thiele, *Phys. Rev. Lett.* **30**, 230 (1973).
- [28] D. J. Clarke, O. A. Tretiakov, G.-W. Chern, Y. B. Bazaliy, and O. Tchernyshyov, *Phys. Rev. B* **78**, 134412 (2008).
- [29] I. A. Ado, O. A. Tretiakov, and M. Titov, *Phys. Rev. B* **95**, 094401 (2017).
- [30] N. Romming, A. Kubetzka, C. Hanneken, K. von Bergmann, and R. Wiesendanger, *Phys. Rev. Lett.* **114**, 177203 (2015).
- [31] W. Voigt, *Lehrbuch der Kristallphysik* (Teubner Leipzig, 1928).
- [32] See <http://www.flapw.de>.
- [33] L. Bellaiche and D. Vanderbilt, *Phys. Rev. B* **61**, 7877 (2000).
- [34] Y. Zhang and W. Yang, *Phys. Rev. Lett.* **80**, 890 (1998).
- [35] J.-P. Hanke, F. Freimuth, S. Blügel, and Y. Mokrousov, *Phys. Rev. B* **91**, 184413 (2015).

- [36] A. A. Mostofi, J. R. Yates, G. Pizzi, Y.-S. Lee, I. Souza, D. Vanderbilt, and N. Marzari, *Comput. Phys. Commun.* **185**, 2309 (2014).
- [37] S. Azzawi, A. Ganguly, M. Tokaç, R. M. Rowan-Robinson, J. Sinha, A. T. Hindmarch, A. Barman, and D. Atkinson, *Phys. Rev. B* **93**, 054402 (2016).
- [38] N.-H. Kim, J. Jung, J. Cho, D.-S. Han, Y. Yin, J.-S. Kim, H. J. M. Swagten, and C.-Y. You, *Appl. Phys. Lett.* **108**, 142406 (2016).
- [39] A. K. Nayak, V. Kumar, T. Ma, P. Werner, E. Pippel, R. Sahoo, F. Damay, U. K. Röbber, C. Felser, and S. S. Parkin, *Nature (London)* **548**, 561 (2017).